



profiltra
customized solutions



PIGMENTS FOR PAINTS AND COATINGS



PAINT

Our portfolio consists of below mentioned organic pigments for the paint industry.

Color Index No.	Heat Stability (°C)	Light Fastness	Acid Resistance	Alcohol Resistance	Alkali Resistance	Oil Resistance	Water Resistance	Liquid decorative / architectural paints	Liquid industrial coatings	Powder coatings	Coil Coatings	Auto Refinish	Auto OEM
PB 15:1	200	8	5	5	5	4 - 5	5	m	l	l			
PB 15:2	200	8	5	4 - 5	5	5	5	m	s	m			
PB 15:3	200	8	5	5	5	5	5	m	m	m	m	s	
PB 15:4	200	8	5	5	5	5	5	m	m	m	s	s	
PG 7	200	8	5	5	5	5	5	m	m	m	s	s	
PO 5	160	6	5	3	5	4	5	m	l				
PO 34	200	6 - 7	5	5	5	4 - 5	5	m	m	m	l		
PO 36	160	8	5	5	5	5	5	m	m	m	s	m	s
PO 43	200	6	5	5	5	5	5	m	s	m	s	s	l
PR 112	180	7 - 8	5	4 - 5	5	4	5	m	s				
PR 122	200	8	5	5	5	5	5	m	m	m	m	m	s
PR 146	180	5 - 6	5	4 - 5	5	5	5	s	s				
PR 170	160	7	5	4 - 5	5	5	5	m	m	s		l	
PR 254	200	8	5	4	5	5	5		m	m	m	m	m
PV 19	200	7 - 8	5	5	5	5	5	m	m	m	m	m	s
PV 23	160	7 - 8	5	4	5	5	5	m	m	m	m	m	s
PY 74	140	7 - 8	5	3 - 4	5	4	5	m	s				
PY 83	200	7 - 8	5	4 - 5	5	5	5	m	m	s			
PY 139	200	8	5	5	5	5	5	m	m	m	s	s	s
PY 151	200	8	5	4 - 5	3	5	5	l	m	m	l	m	l
PY 154	200	8	5	5	5	5	5	m	m	m	l	m	s
PY 194	200	8	5	4	5	4 - 5	5	m	m	m	l	l	

Heat stability: 30 minutes baking time
 Light fastness: tested in accordance to DIN EN ISO 105-B01
 Resistance to solvent: tested in accordance to DIN EN ISO 105-A02
 Resistance to oil: tested in accordance to DIN EN 20105-A03

m = main application
 s = suitable
 l = limited suitable